

IN THE SPECIFICATION

Please amend Table 3 on page 72 as follows:

Table 3

	Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4	Comparative Example 5	Comparative Example 6	Comparative Example 7
Polymer composition (part by mass)							
(a) Block copolymer	30	24	70	27 27	70	54	35
Block copolymer 1							
Block copolymer 3							
Block copolymer 5							
(b) Acrylic resin							
Acrylic resin 1	70	56		18	30	36	23
Acrylic resin 2							
(c) Softener C-1							
Diana Process PW-380		20	30	55		10	42
Scratch resistance ( $\mu\text{m}$ )	15	19	9.8	20	10.9	12.5	11.6
Taber abrasion ( $\text{mm}^3$ )	230	272	321	>500	412	453	248
Total transmittance (%)	82.6	87.0	91.7	92.2	83.4	87.8	67.1
Tensile permanent set (%)	Fracture	5.0	0.0	0.0	4.7	4.0	5.0
Hardness (Type A)	98	82	38	8	85	70	55
Breaking strength (MPa)	5.1	9.8	22.4	5.0	15.2	13.1	77
MFR (g/10min)	57	>100	61	>100	0.6	1.9	0.1
Dispersed particle size ( $\mu\text{m}$ )	N/A	N/A	-	0.80	0.21	0.18	N/A